

# Closed Cell Cross-Link Polyethylene

## Description:

This expansion joint material is extruded from a high quality closed cell, cross-linked polyethylene foam.

**Cross-Link Polyethylene** provides all the same reliable characteristics of standard non-cross-link polyethylene, but is compatible with hot applied sealants and exposure to a broader range of solvents.

**Cross-Link Polyethylene** is available with or without a peel off top.

## Use:

**Cross-Link Polyethylene** expansion joint filler can be used in all standard concrete construction, such as highways, runways, parking garages, driveways, sidewalks, and floor slabs.

**Cross-Link Polyethylene** can also be used as a buffer between dissimilar materials such as columns, manhole covers, and adjacent constructions.

## Features:

- Extruded from a high quality, closed cell Cross-linked polyethylene foam
- **Tear-Off Strip** – Available upon request, but can be special ordered without
- **Flexibility** – Will not break or crack when used around curves or columns
- **Accepted** – Currently used by both residential and commercial contractors
- **Durable** – With near zero water absorption, Cross-link polyethylene will not rot over time
- **Economical** – Easily cut and handled on any jobsite

Physical Properties	Value*	Test Method
Material	Polyethylene	**Testing done according to ASTM D3575 and ASTM C117 (thermal conductivity) Standards.
Color	Charcoal	
Density, Apr. (lbs/ft <sup>3</sup> )	2.0 PFC	
Tensile Strength (psi min)	43 PSI	
Elongation at Break (% min)	120%	
Water Absorption	<0.06	
Compression Set (% of original thickness)	24%	
Tear Strength	11 (lb/in)	
Compressive Strength (@ 25% PSI)	6 PSI	
Thermal Stability (% of change @ 158° for 24 hrs)	<0.5	
Thermal Conductivity (btu / hr / ft <sup>2</sup> °F)	0.26	
Working Temp. Range	-70°F - 410°F	
Flammability (MVSS302)	Pass Available	

ASTM-D-4819 Type I  
ASTM-D-1752 Modified, Section 5.1 – 5.4\*  
ASTM-D-5249, Type II

While values shown are typical of these products, they should not be construed as specification limits.



6553 West 400 North • Greenfield IN • 46140

Ph: (317)891-1010 • Fx: (317)891-1019 • Toll Free: (800)253-4237

On the web: [www.nmwinc.com](http://www.nmwinc.com)